

OBTEX-BA

Product Details:

OBTEX- BA Powder is a highly substantive optical whitening agent for all natural and regenerated cellulosic fibres except acetate. It is also applied on Pulp having sized in alkaline medium with synthetic sizing additives. The product is not suitable in surface sizing application.

Properties:

Appearance	Yellowish Powder.
Chemical composition	Stilbene Disuphonic Acid derivative.
Ionic Character	Anionic.
Storage Stability	12 Months.
Stability	Water : Very good Hydrosulphite : Very good Chlorine : Not stable Acid : Not stable under 5
Shade	Bluish to Neutral White.
pH at 25°C	9.5 ± 0.5
Bulk Density	0.60 ± 0.01
Hard Water	Upto 70 ppm
Type	Disulpho.

It can be dissolved very quickly by adding an equal amount of hot distilled softened water to form an aqueous solution which remains clear and does not gel when cooled. It is advisable to boil up the solution immediately before adding to the treatment baths or in the Paper Machine chests. When preparing stock solutions of OBTEX- BA Powder Powder, soft or dematerialized water should be used, as hard water may cause precipitation.

Shade :

The shade of white effects is obtained in alkaline medium.

Fastness Stability :

When the white effects are acidified the shade may tend to yellow but this can be remedied by a weakly alkaline rinse. Hard water has no adverse influence on the white effect. In fact, it produces a quicker and more complete exhaustion of the bath.

However, iron and, to a fastness extent, copper compounds impair the white effect and treatment may only be carried out on machines of these metals if the surfaces have been rendered inert.

Solutions of OBTEX- BA Powder are sensitive to light. Stock solutions must therefore be kept away from light.



Plot No.C1B 3420, PCI Chokdi,
GIDC Estate, Ankleshwar-393002(Guj.)
+91 99980 42948, +91 94261 38510
info@sunwhitechemicals.com
www.sunwhitechemicals.com



Toxicology :

Lethal dose in rats (LD50) is about 5300 mg/kg body weight. Tests on rabbits showed that there was no irritation on the skin or mucous membranes. This product is partially eliminated by the micro-organisms in activated sludge and does not impair their effectiveness in amounts up to 300 mg/l. Trout withstand up to 1000 mg/l on brief exposure (48 hours).

The above information and recommendation contained in this data sheet are based on the present state and best of our knowledge and belief. Our suggestion does not release you from the obligation to check its validity and to test our products as to its suitability for the intended process and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical guidelines are beyond of our control.